

(12) INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

(19) World Intellectual Property

Organization

International Bureau



WIPO | PCT



(10) International Publication Number

WO 2014/188158 A1

(43) International Publication Date  
27 November 2014 (27.11.2014)

(51) International Patent Classification:

B01J 20/26 (2006.01) C08J 5/20 (2006.01)  
C22B 3/24 (2006.01) C08F 6/02 (2006.01)  
C22B 7/00 (2006.01) C08J 9/26 (2006.01)  
C08F 2/44 (2006.01) C08F 6/28 (2006.01)  
B01J 39/20 (2006.01) C22B 3/20 (2006.01)  
C02F 1/56 (2006.01) B01J 41/14 (2006.01)

(21) International Application Number:

PCT/GB2014/051390

(22) International Filing Date:

6 May 2014 (06.05.2014)

(25) Filing Language:

English

(26) Publication Language:

English

(30) Priority Data:

1309308.3 23 May 2013 (23.05.2013) GB

(71) Applicant: THE UNIVERSITY OF LINCOLN  
[GB/GB]; Faculty of Health, Life & Social Science, Bray-  
ford Pool, Lincoln Lincolnshire LN6 7TS (GB).

(72) Inventor: GONZALEZ-RODRIGUEZ, Jose;

(81) Designated States (unless otherwise indicated, for every

kind of national protection available): AE, AG, AL, AM, AO, AT, AU, AZ, BA, BB, BG, BH, BN, BR, BW, BY, BZ, CA, CH, CL, CN, CO, CR, CU, CZ, DE, DK, DM, DO, DZ, EC, EE, EG, ES, FI, GB, GD, GE, GH, GM, GT, HN, HR, HU, ID, IL, IN, IR, IS, JP, KE, KG, KN, KP, KR, KZ, LA, LC, LK, LR, LS, LT, LU, LY, MA, MD, ME, MG, MK, MN, MW, MX, MY, MZ, NA, NG, NI, NO, NZ, OM, PA, PE, PG, PH, PL, PT, QA, RO, RS, RU, RW, SA, SC, SD, SE, SG, SK, SL, SM, ST, SV, SY, TH, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, ZA, ZM, ZW.

(84) Designated States (unless otherwise indicated, for every kind of regional protection available): ARIPO (BW, GH, GM, KE, LR, LS, MW, MZ, NA, RW, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian (AM, AZ, BY, KG, KZ, RU, TJ, TM), European (AL, AT, BE, BG, CH, CY, CZ, DE, DK, EE, ES, FI, FR, GB, GR, HR, HU, IE, IS, IT, LT, LU, LV, MC, MK, MT, NL, NO, PL, PT, RO, RS, SE, SI, SK, SM, TR), OAPI (BF, BJ, CF, CG, CI, CM, GA, GN, GQ, GW, KM, ML, MR, NE, SN, TD, TG).

Published:

— with international search report (Art. 21(3))

(74) Agent: LOVEN PATENTS & TRADEMARKS LIM-  
ITED; 3 Checkpoint Court, Lincoln, Lincolnshire, LN6  
3PW (GB).

(54) Title: METALS RECOVERY METHOD AND POLYMER FOR USE IN METALS RE-COVERY AND PROCESS FOR MAKING SUCH A POLYMER

(57) Abstract: A process of forming a porous polymer template material for use in selectively recovering a metal from a solution of the metal ions comprises polymerising a monomer admixed with a compound of the metal to be recovered, and then treating the polymer to remove the metal compound therefrom. A method of selectively recovering a metal from a solution containing the metal ions comprises contacting a polymer template material formed by a process according to any preceding claim with the solution containing the metal ions, and recovering the metal from the polymer. The invention also proves a polymeric material adapted to capture from a solution containing ions of plural metals a specific one of the metals.

WO 2014/188158 A1

- 1 -

## **METALS RECOVERY METHOD AND POLYMER FOR USE IN METALS RECOVERY AND PROCESS FOR MAKING SUCH A POLYMER**

### **Field of the Invention**

**[0001]** This invention relates to a method of recovering high-value metals  
5 such as rhenium from superalloys, a process for making a polymer for use in a metals recovery method, and a polymer adapted for such use.

### **Background to the Invention**

**[0002]** Superalloys are metallic materials with a basic composition of nickel and cobalt or nickel and iron which, combined with other metals, form a highly  
10 resistant material. Use of metals such as rhenium in superalloys confers extraordinary properties to these alloys, such as increased resistance to corrosion and mechanical strength.

**[0003]** Recycling of rhenium from superalloys is an emerging market, with very little recycling actually being carried out currently using scrap super alloy or  
15 other alloys, or usually discarded production material.

**[0004]** Concerns and fluctuations in the mined supply of Rhenium are the main driving force behind its recycling. This is due to the fact that mining for Rhenium *per se* is not economically viable; it is actually a by-product of Copper and Molybdenum mining. If the price of either of these metals falls to an uneconomic  
20 level, the mine is closed. The U.S. Geological Survey Mineral Commodity Summaries in January 2008 identified the World reserves of this metal to be around 10 million kilograms.

**[0005]** It is known that the current recycling methods employed are quite long (at 6 – 9 months). The properties that the alloy is designed to offer, i.e.  
25 high strength, toughness and extraordinary wear resistance, make it a very difficult substance to work with. The preparation of super alloys for Rhenium recycling involves processes that specifically grind these materials. The actual decomposition in turn is carried out by wet chemistry involving heat treatment in mineral acids. This is followed by solvent extraction combined with sulphide  
30 precipitation and electro-deposition. Current costs for the process are in the region of \$3000 per kg Rhenium recovered, with yields of around 70%. To be

- 2 -

commercially attractive, an innovation to recycle rhenium requires added value by reducing the time constraints, reducing costs, increasing yields or a combination of the previous ones.

5     **[0006]**     The present invention includes the manufacturing process of a polymeric material able to trap rhenium in order to obtain highly purified extracts of this metal in a short period of time.

### **Summary of the Invention**

10     **[0007]**     The invention provides a process for forming a porous polymer template material for use in selectively recovering a metal from a solution of the metal ions, comprising polymerising a monomer admixed with a compound of the metal to be recovered, and then treating the polymer to remove the metal compound therefrom.

15     **[0008]**     Preferably, the template material is formed by cross-linking a monomer in the presence of a porogen and said metal compound.

20     **[0009]**     The invention also provides a method of selectively recovering a metal from a solution containing the metal ions, comprising contacting a polymer template material formed by a process according to the invention with the solution containing the metal ions, and recovering the metal from the polymer. The selectivity of the polymer for a specific metal enables an aqueous solution of mixed metal ions, in which the metal of interest may be a minor constituent, to be treated economically.

25     **[0010]**     The invention further provides a polymeric material adapted to capture from a solution containing ions of plural metals a specific one of the metals.

### **Detailed Description of the Invention**

30     **[0011]**     The general manufacturing process of the polymer used in the recycling of solutions with an important rhenium content involves the creation of a carbon lattice using a monomer, a cross-linker, initiator and a porogen and the use of a rhenium compound to create a template that is imprinted into this synthetic carbon polymeric material. Following the key-lock principle the rhenium

- 3 -

compound found in a concentrated solution of this metal will be trapped selectively and the rest of the solution will be eluted unaffected.

**[0012]** The general process of manufacturing involves the production of the template using a rhenium salt, namely ammonium perrhenate, with a rhenium concentration ranging between 10-250mg/mL to control the trapping capacity of the polymer. These amounts can be increased to obtain higher yields.

**[0013]** The polymer is manufactured using the following proportions: 5-9% template (such as a rhenium salt), 2-6% monomer (such as vinylpyridine), 42-54% porogen (such as chloroform) and 35-45% of crosslinker (such as Ethyleneglycoldimethacrylate). To finalise the reaction mixture, 90-150mg of initiator (such as 1,1'-azobis(cyclohexanecarbonitrile)) is added to the container.

**[0014]** Once all the chemicals have been added to the reaction container the mixture is vortexed for a period of time not less than 2 minutes. After the complete mixture has been homogenised a flow of nitrogen is pumped into the solution to eliminate all traces of oxygen that might be present for no less than 10 minutes. Once the solution has been purged with Nitrogen, the container is then sealed and then placed in an oven for not less than 48hours, at a temperature of 70°C to allow the solution to polymerise. As the pressure within the container is likely to increase, the material used for the container needs to be able to withstand high pressures.

**[0015]** After the polymerisation is completed the solid polymer is removed from the glass vial and crushed into smaller particles mechanically with aids of mortar and pestle or a ball mill until the particle size is homogenous and the material reaches a sand-type texture.

**[0016]** Once the material has been produced is placed in a column or in a container as the template has to be removed to make it functional and ready to trap rhenium. The template is dislodged by adding to the column or to the container where the material is kept, a 8M solution of hydrochloric acid (pH=-0.8) and left for 20-30 min until all the template has been removed. The final conditioning consists of a washing process of the polymer until the pH of the eluents

- 4 -

reach values close to 6-7. A new addition of a solution containing rhenium at pH close to neutrality will result in rhenium being trapped.

**[0017]** The material can be re-used without loss of the trapping properties or damage to its structure for at least 5 cycles (number tested) but it is believed  
5 the durability goes beyond this number of cycles.

**[0018]** Using X-ray Fluorescence (XRF) the molecular imprinted polymer (MIP) could be analysed to determine the percentage of rhenium present within the solid MIP when samples of rhenium solution were eluted through, determining how much rhenium has been trapped by the polymer. Also Fourier transform infrared spectroscopy (FTIR) was also used to determine whether or not  
10 rhenium is trapped in the MIP at a wavenumber of 900 cm<sup>-1</sup>.

**[0019]** It has also been proven that the MIP traps rhenium in a selective way. A solution containing seven different metals present in a typical alloy is proven to retain only rhenium when processed and eluted through the MIP when analysed using XRF.  
15

**CLAIMS**

1. A process of forming a porous polymer template material for use in selectively recovering a metal from a solution of the metal ions, comprising polymerising a monomer admixed with a compound of the metal to be recovered, and then treating the polymer to remove the metal compound therefrom.  
5
2. A process according to Claim 1, wherein the template material is formed by cross-linking a monomer in the presence of a porogen and said metal compound.
3. A process according to Claim 2, wherein the metal compound is a salt.  
10
4. A process according to any preceding claim, comprising comminuting the polymer after formation.
5. A process according to Claim 2 or 3, wherein the monomer is vinylpyridine.
6. A process according to Claim 5, wherein the porogen is chloroform.  
15
7. A process according to any preceding claim, wherein the polymer is treated with acid to remove the metal compound.
8. A process according to Claim 7, wherein the acid is concentrated hydrochloric acid.  
20
9. A process according to any preceding claim, wherein the metal is rhenium.
10. A process according to Claim 9, wherein the metal compound is ammonium perrhenate.
11. A method of selectively recovering a metal from a solution containing the metal ions, comprising contacting a polymer template material formed by a process according to any preceding claim with the solution containing the metal ions, and recovering the metal from the polymer.  
25
12. A method according to Claim 11, wherein the recovering step comprises treatment of the polymer template material with acid.  
30
13. A method according to Claim 12, wherein the acid is concentrated hydrochloric acid.

## INTERNATIONAL SEARCH REPORT

International application No

PCT/GB2014/051390

## A. CLASSIFICATION OF SUBJECT MATTER

INV. B01J20/26 C22B3/24 C22B7/00 C08F2/44 B01J39/20  
 C02F1/56 C08J5/20 C08F6/02 C08J9/26 C08F6/28  
 C22B3/20 B01J41/14

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

B01J C22B C08F C02F C08J

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)

EPO-Internal, WPI Data

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	CN 102 068 968 A (UNIV DALIAN OCEAN) 25 May 2011 (2011-05-25)	1-8, 11-13
Y	abstract; claims 1,2 -----	9,10
X	KR 2012 0065848 A (RES & BUSINESS FOUNDATION SUNGKYUNKWAN UNIVERSITY [KR]) 21 June 2012 (2012-06-21)	1-8, 11-13
Y	paragraphs [0001], [0024] - [0036] -----	9,10
X	KR 2010 0089621 A (UNIV SUNGKYUNKWAN FOUND [KR]) 12 August 2010 (2010-08-12)	1-8, 11-13
Y	claims 1-17; examples 1,2 -----	9,10
X	WO 2007/055767 A1 (UNIV JOHNS HOPKINS [US]; MURRAY GEORGE M [US]; VAN HOUTEN KELLY A [US]) 18 May 2007 (2007-05-18)	1-8, 11-13
Y	paragraphs [0013] - [0016], [0035] - [0038]; claims 1-35; examples 1-7 -----	9,10
	-/--	

☒ Further documents are listed in the continuation of Box C.☒ See patent family annex.

\* Special categories of cited documents :

"A" document defining the general state of the art which is not considered to be of particular relevance

"E" earlier application or patent but published on or after the international filing date

"L" document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)

"O" document referring to an oral disclosure, use, exhibition or other means

"P" document published prior to the international filing date but later than the priority date claimed

"T" later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention

"X" document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone

"Y" document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art

"&amp;" document member of the same patent family

Date of the actual completion of the international search

22 August 2014

Date of mailing of the international search report

02/09/2014

Name and mailing address of the ISA/

European Patent Office, P.B. 5818 Patentlaan 2  
 NL - 2280 HV Rijswijk  
 Tel. (+31-70) 340-2040,  
 Fax: (+31-70) 340-3016

Authorized officer

Gold, Josef



## INTERNATIONAL SEARCH REPORT

International application No

PCT/GB2014/051390

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	WO 2013/063772 A1 (EMPIRE TECHNOLOGY DEV LLC [US]; HU XIAOBIN [CN]) 10 May 2013 (2013-05-10)	1-8, 11-13
Y	paragraphs [0033], [0034]; claims 1-18; example 1 -----	9,10
Y	US 7 704 908 B2 (MATUSZ MAREK [US] ET AL) 27 April 2010 (2010-04-27)	9,10
A	column 3, line 41 - column 6, line 29; claims 1-27; examples 1-4 -----	1-8, 11-13
X	J0 S H ET AL: "Continuous separation of copper ions from a mixture of heavy metal ions using a three-zone carousel process packed with metal ion-imprinted polymer", JOURNAL OF CHROMATOGRAPHY, ELSEVIER SCIENCE PUBLISHERS B.V, NL, vol. 1217, no. 45, 5 November 2010 (2010-11-05), pages 7100-7108, XP027418027, ISSN: 0021-9673 [retrieved on 2010-09-21] page 7101 - page 7108 -----	1-13
X	SE-HEE J0 ET AL: "Development of a four-zone carousel process packed with metal ion-imprinted polymer for continuous separation of copper ions from manganese ions, cobalt ions, and the constituent metal ions of the buffer solution used as eluent", JOURNAL OF CHROMATOGRAPHY, ELSEVIER SCIENCE PUBLISHERS B.V, NL, vol. 1218, no. 33, 26 June 2011 (2011-06-26), pages 5664-5674, XP028247421, ISSN: 0021-9673, DOI: 10.1016/J.CHROMA.2011.06.094 [retrieved on 2011-07-03] page 5664 - page 5674 -----	1-13
Y	GIANCARLA ALBERTI ET AL: "Supramolecular receptors in solid phase: developing sensors for anionic radionuclides", DALTON TRANSACTIONS, vol. 42, no. 17, 17 December 2012 (2012-12-17), page 6227, XP055135894, ISSN: 1477-9226, DOI: 10.1039/c2dt32211k page 6227 - page 6233 ----- -/--	9,10



## INTERNATIONAL SEARCH REPORT

International application No

PCT/GB2014/051390

C(Continuation). DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
X	GAZI TÜRKÖGLÜ, CHRISTINA PUBILL ULLDEMOLINS, RAINER MÜLLER, EIKE HÜBNER, FRANK W. HEINEMANN, MARION WOLF, NICOLAI BURZLAFF: "Bis(3,5-dimethyl-4-vinylpyrazol-1-yl)acet ic Acid: A new Heteroscorpionate Building Block for Copolymers that Mimic the 2-His-1-carboxylate Facial Triad", EUROPEAN JOURNAL OF INORGANIC CHEMISTRY, vol. 2010, 14 May 2010 (2010-05-14), pages 2962-2974, XP002728794, DOI: DOI: 10.1002/EJIC.201000115	1-9, 11-13
Y	page 2962 - page 2974 -----	10

# INTERNATIONAL SEARCH REPORT

Information on patent family members

International application No

PCT/GB2014/051390

Patent document cited in search report	Publication date	Patent family member(s)	Publication date
CN 102068968 A	25-05-2011	NONE	
KR 20120065848 A	21-06-2012	NONE	
KR 20100089621 A	12-08-2010	NONE	
WO 2007055767 A1	18-05-2007	AU 2006312273 A1 CA 2624460 A1 EP 1948357 A1 JP 2009515696 A US 2008264868 A1 US 2012012530 A1 WO 2007055767 A1	18-05-2007 18-05-2007 30-07-2008 16-04-2009 30-10-2008 19-01-2012 18-05-2007
WO 2013063772 A1	10-05-2013	CN 103842390 A US 2014186970 A1 WO 2013063772 A1	04-06-2014 03-07-2014 10-05-2013
US 7704908 B2	27-04-2010	NONE	